

Product Data Sheet
Edition 18/07/2007
Identification no:
02 09 01 05 001 0 000000
Sika® WP Shield-103 PS

Sika® WP Shield-103 PS

APP modified bituminous membranes –sand finish

Product Description	APP modified Bituminous Polyester reinforced waterproofing membrane manufactured from a rich mixture of bitumen and selected polymers blended together to obtain excellent heat resistant, flexibility, UV resistance. Modified bitumen then coated onto a dimensionally stable carrier to obtain excellent tensile strength, tear and puncture resistance. A layer of natural river sand is added as a top layer.
Uses	■ It is used as waterproofing /dam proofing membrane for protection of various substrates in wide range of applications.
Characteristics / Advantages	
Tests	
Approval / Standards	Conforms to : UEAtc,ASTM D146, DIN52123, ASTM D36, ASTM D5, UEAtc, ASTM D 5147, ASTM D4799

Product Data

Form	
Appearance / Colours	Black membrane
Packaging	1.0 x 10 m roll

Storage

Storage Conditions / Shelf-Life	Rolls must be stored in their original package, in horizontal position and under cool and dry conditions. They must be protected from direct sunlight, rain, snow and ice, etc. Should be stored vertically in clean covered one. Rolls should be etched.
--	---

Technical Data

Chemical Base	APP modified Bituminous Polyester
Thickness	3mm
Unit weight	3.3 kg/m ² (According to UEAtc)

Mechanical / Physical Properties

Tensile Strength (L/T)N/SCM	650/500 (According to UEAtc,ASTM D146)
Elongation at break (L/T)	40/45 (According to UEAtc,ASTM D146)



Resistance to water pressure	No leakage	(According to DIN52123)
Carrier (Polyster) weight	160 g/m ²	
Softening Point	145 °C	(According to ASTM D36)
Penetration	15-25 at 25°C d mm	(According to ASTM D5)
Tear resistance (L/T)N	150/170	(According to UEAtc)
Water Absorption% (BSP)	<0.15	(According to ASTM D 5147)
Heat Resistance	No Flow at 100°C	
Resistance to Aging after 2000hrs	No Delamination	(According to ASTM D4799)
(Weather –O- Meter)		

System Information

Application Details

Substrate Quality Concrete, mortar surfaces must be clean, free from grease, oil, and loosely adhering particles. Steel and iron surfaces must be free from scale, rust, grease and oil. All surfaces must be as true as possible.

Application Conditions / Limitations

Substrate Temperature +10°C min. / +40°C max.

Ambient Temperature +10°C min. / +40°C max.

Application Instructions

Application Method / Tools Application procedure may vary slightly depending upon site conditions. However given below are general guidelines.

Apply bituminous primer to a clean, smooth and dry surface by brush, roller or spray. Unroll and align and re roll correctly before torching. Overlaps should be minimum 100mm. Use gas burner to heat the substrate and thermo fusible film on the underside on lower face of membrane. When the thermo- fusible film melts after torching, the membrane is ready to stick. Roll forward and press firmly against the substrate to bond. Heat both the overlaps and use the round tipped trowel heating the same to smoothen and press into seam.

All angles and abutments should be sealed with extra care to ensure full bondage. The edges should be sealed well into the grooves.

Value Base

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



Sika India Pvt. Ltd.
Commercial Complex II
620, Diamond Harbour Road
Kolkata, 700 034, India

Phone +91 33 2447 2448/2449
Telefax +91 33 2468 8688/2665
www.sika.in
info@in.sika.com